

Test laboratory for the fire behavior of building materials, Dipl.-Ing. (FH) Andreas Hoch
Testing, supervising and certifying body, authorized by the building supervision authority

TEST REPORT

PZ-Hoch-221105

for the proof of Fire behaviour according to DIN 4102, part 1

Translation of the German test report – no guarantee for translation of technical terms

company	Brand Management Group 1605 Main St., Suite 300 Sarasota, FL 34236 USA
description of samples	polyester fabric made from recycled polyester with adhesive film on one side and polymer coating on the other side
name of the material	„HP Recycled Removable Adhesive Fabric (Latex/Solvent)“
sampling	by the company itself
content of request	Proof of flammability to classify building materials to class B1 “schwerentflammbar” according to DIN 4102, part 1
validity of test report	31.10.2027
result	The examined product meets glued on massive mineral substrates with a density of $\geq 1.500 \text{ kg/m}^3$ and thickness of $\geq 0,6\text{mm}$ the requirements of class B1 for “schwerentflammbare” (hardly flammable) building materials according to DIN 4102, part 1 (May 1998).

This test report includes 4 pages and 5 enclosures.

Remark: If the above mentioned building material is not used as product according to MBO § 2, Abs. 9, Ziffer1, there is no need for a general building supervisory test report.

This test report is not valid if the examined building material is used as product in the meaning of state building prescriptions (MBO § 17, Abs. 3).

This test report does not replace an eventually necessary proof of applicability concerning building supervisory or building laws in the meaning of state building prescriptions. This has to be verified by:

- “allgemeine bauaufsichtliche Zulassung” (general building inspectorate approval) or by
- „allgemeines bauaufsichtliches Prüfzeugnis“ (general building inspectorate certificate) or by
- “Zustimmung im Einzelfall” (exceptional approval)

This test report can underlie building supervisory procedures

- for regular building products for the prescribed proofs of conformity
- for non-regular building products for the needed proofs of applicability.

This test report must not be published and copied without preceding agreement of the test laboratory and if agreed, only during validity and unchanged concerning appearance and contents.

1. Description of test material in condition as delivered

PN 35821: „HP Recycled Removable Adhesive Fabric (Latex/Solvent)“

-polyester fabric made from recycled polyester from water bottles with adhesive film and protection film on one side and polymer coating on the other side-
front side: white, coated / reverse side: self-adhesive

characteristic values determined by the test laboratory:

whole thickness: about 0,32 mm
whole area weight: about 326 g/m²
thickness of self-adhesive foil: about 0,16 mm
area weight of self-adhesive foil: about 186 g/m²

The testing laboratory is not provided with further details concerning composition of the tested building materials. Samples are deposited.

2. Preparation of samples

The samples were kept in climate chamber 23/50 until they reached constant weight.
The self-adhesive film was glued on fiber cement boards with a thickness of about 6 mm, according to DIN 4102-16: 2015-09, point 4.4, a.

3. Arrangement of samples

#5796: flaming in machine direction, glued on fiber cement boards
#5797: flaming in transverse direction, glued on fiber cement boards
#5919: flaming in transverse direction, glued on fiber cement boards
#5920: flaming in transverse direction, glued on fiber cement boards

4. Date of test CW 42 and CW 48 in 2022

5. Results The test has been examined according to DIN 4102 (Mai 1998)

line no.	Measurement	Result with the tested specimen					Dim.
		#5796	#5797	#5919	#5920	---	
	Test number	#5796	#5797	#5919	#5920	---	
	flamed direction substrate	machine dir. fiber cement board	transv. dir. fiber cement board	machine dir. fiber cement board	transv. dir. fiber cement board	---	
1	<u>Number of specimen arrangement</u> acc. to. DIN 4102/T15, schedule 1	7	7	7	7	---	
2	<u>Maximum flame height above bottom</u> edge of the specimen	50	70	60	60	---	cm
3	Time ¹⁾	0:18	6:50	7:40	4:10	---	min:s
4	<u>Burn through / melting</u> Time ¹⁾	./.	./.	./.	./.	---	min:s
	<u>Observations on the back side of the</u> <u>specimen</u>						
5	Flames / Glowing Time ¹⁾	---	---	---	---	./. ./.	min:s
6	Change of colour Time ¹⁾	---	---	---	---	./. ./.	min:s
7	<u>Falling of burning droplets</u> Start ¹⁾	./. ./.	./. ./.	./. ./.	./. ./.	./. ./.	min:s
8	sporadic falling of burning droplets ²⁾	---	---	---	---	./. ./.	
9	continuous falling of burning droplets ²⁾	./. ./.	./. ./.	./. ./.	./. ./.	./. ./.	min:s

line no.	Measurement	Result with the tested specimen					Dim.
		#5796	#5797	#5919	#5920	---	
	Test number						
	flamed direction substrate	machine dir. fiber cement board	transv. dir. fiber cement board	machine dir. fiber cement board	transv. dir. fiber cement board	---	
10	<u>Falling of burning droplets</u> Start ¹⁾	./.	./.	./.	./.	./.	min:s
11	Extent	./.	./.	./.	./.	./.	
12	sporadic falling of burning droplets ²⁾ continuous falling of burning droplets ²⁾	./.	./.	./.	./.	./.	
13	<u>After flame time at the bottom of the sieve (max.)</u>	./.	./.	./.	./.	./.	min:s
14	<u>Impairment of the burner by dropping or falling material:</u> Time ¹⁾	./.	./.	./.	./.	./.	min:s
15	<u>Premature end of test</u> Final occurrence of burning at the specimen ¹⁾	06:50	10:49	10:00	08:45	./.	min:s
16	Time of eventually end of test ¹⁾	./.	./.	./.	./.	./.	min:s
17	<u>After flame after end of test</u> Time ¹⁾	./.	./.	./.	./.	./.	min:s
18	Number of specimen	./.	./.	./.	./.	./.	
19	Front side of specimen ²⁾	./.	./.	./.	./.	./.	
20	Back side of specimen ²⁾	./.	./.	./.	./.	./.	
21	flame length	./.	./.	./.	./.	./.	
22	<u>Afterglow after end of test</u> Time ¹⁾	./.	./.	./.	./.	./.	min:s
23	Number of specimen	./.	./.	./.	./.	./.	
	<u>Place of appearance</u>	./.	./.	./.	./.	./.	
24	Lower half of the specimen ²⁾	./.	./.	./.	./.	./.	
25	Upper half of the specimen ²⁾	./.	./.	./.	./.	./.	
26	Front side of specimen ²⁾	./.	./.	./.	./.	./.	
27	Back side of specimen ²⁾	./.	./.	./.	./.	./.	
28	<u>Density of smoke</u> ≤ 400 % * min	10	9	8	7	---	% * min
29	> 400 % * min ⁴⁾	./.	./.	./.	./.	./.	% * min
30	Diagram: encl. no.	1	2	3	4	---	
31	<u>Residual lengths: individual value ³⁾</u>						
	Specimen 1	45	43	43	40	---	cm
	Specimen 2	42	45	37	30	---	cm
	Specimen 3	47	43	39	37	---	cm
	Specimen 4	48	38	37	32	---	cm
32	<u>Average value, individual test ³⁾</u>	46	42	39	35	---	
33	<u>Photo of specimen in enclosure no.</u>	1	2	3	4	---	
34	<u>Flue gas temperature</u>	121	117	113	115	---	°C
35	<u>Maximum of average value</u> Time ¹⁾	09:08	10:00	09:15	09:11	---	min:s
36	Diagram: encl. no.	1	2	3	4	---	

¹⁾ indication of times: from the begin of testing procedure

²⁾ checked off if applicable

³⁾ indication of carrier/foam layer separated in case of fire-proofing agents

⁴⁾ very strong development of smoke

6. Explanations concerning the testing procedure

-none-

7. Summary of results and additional establishments to Fire Behaviour

line no.	measurement test-no.	Result with the tested specimen					dimension
		#5796	#5797	#5919	#5920	---	
	flamed direction substrate	machine dir. fiber cement board	transv. dir. fiber cement board	machine dir. fiber cement board	transv. dir. fiber cement board	---	
1	residual length	46	42	39	35	---	cm
2	max. smoke temperature	121	117	113	115	---	°C
3	density of smoke - integral	10	9	8	7	--	%min
4	remarks: -none-						

According to DIN 4102, part 1, "schwerentflammbare" (hardly flammable) building materials must meet the requirements of class B2.

Pursuant to additional tests in the ignitability apparatus this can be determined (appendix 5).

8. Special remarks

- This report is only valid for the material as described under paragraph 1. In combination with other materials or with additional coatings or grounds etc. the burning behaviour may differ.
- This test report is not valid for the exposure to outdoor climate conditions.
- This test report is not valid, as soon as the fabric is used as a building product in the sense of the "Landesbauordnungen" (state building requirements, MBO § 17, par. 3).
- This test report is no substitute for a General Building Inspectorate Certificate.
- This test report is granted without prejudice to the rights of third parties, in particular private proprietary rights.
- For legal interests only the German original version is relevant.
- In General Building Inspectorates procedures this test report can be based for
 - regular building materials for the required proof of accordance
 - for not regular building materials for the required proof of applicability

9. Validity

This test report is valid until the mentioned date on page 1. The test report becomes invalid in case the standards on which the tests are based are changed.

Fladungen, 05.12.2022

clerk in charge:



(Dipl.-Ing.(FH) Jürgen Hammer)




Head of the test laboratory:




(Dipl.-Ing.(FH) Andreas Hoch)

„Brandschacht“-test #5796




measurement

#5796, PN35821: "HP Recycled Removable Adhesive Fabric", L
 Max. flue temperature: 121°C, Smoke density integral: 10%min
 Residual length: 46 cm




„Brandschacht“-test #5797




measurement

#5797, PN35821: "HP Recycled Removable Adhesive Fabric", Q
 Max. flue temperature: 117°C, Smoke density integral: 9%/min
 Residual length: 42 cm




„Brandschacht“-test #5919



measurement

#5919, PN35821: "HP Recycled Removable Adhesive Fabric", Q
 Max. flue temperature: 113°C, Smoke density integral: 8%min
 Residual length: 39 cm




„Brandschacht“-test #5920



measurement

#5920, PN35821: "HP Recycled Removable Adhesive Fabric", Q
Max. flue temperature: 115°C, Smoke density integral: 7%min
Residual length: 35 cm



**Test for normal flammability
classifying B2 according to DIN 4102**

1. Description of test material in condition as delivered look at page 2

2. Preparation of samples

Out of the material there have been cut samples for the ignitability apparatus.
The samples were kept in a climate 23/50 until they reached constant weight.

3. Arrangement of samples -glued on fiber cement boards-
Flaming in machine and in transverse direction

4. Date of test CW 42 in 2022

5. Results

PN 35821:	edge-test						surface-test						Dim
samples no.	1	2	3	4	5	6	1	2	3	4	5	6	
ignition ¹⁾	1	1	1	1	1	--	10	10	--	--	--	--	s
reaching the mark of measurement ¹⁾²⁾	-/-	-/-	-/-	-/-	-/-	--	-/-	-/-	--	--	--	--	s
max. flame height	4	4	4	4	4	--	3	3	--	--	--	--	cm
Time	12	12	12	12	11	--	14	13	--	--	--	--	
self-cessation of the flames end of afterflame ¹⁾	15	15	15	15	15	--	15	15	--	--	--	--	s
end of glowing ¹⁾	-/-	-/-	-/-	-/-	-/-	--	-/-	-/-	--	--	--	--	s
flames were extinguished after ¹⁾	-/-	-/-	-/-	-/-	-/-	--	-/-	-/-	--	--	--	--	
smoke development (visual)	little						little						./.
dropping of burning material during 20 s ¹⁾	-/-	-/-	-/-	-/-	-/-	--	-/-	--	--	--	--	--	s
Appearance after test: burned out till max. height 3 cm x width 1,5 cm													

¹⁾ time mentioned from the beginning of the test ²⁾ during 20 Sec -/- no appearance -- no information

6. Remarks and explanations to the testing procedure

-none-

7. Opinion concerning the dropping of burning material

The test for normal flammability shows no burning dripping material.